

Technical Data Sheet



OCI E-104 ACETIC CURE SILICONE SEALANT

Physical Data :

Unvulcanized Rubber

Density at 25 °C	:	1.03 g/cm ³ +/- 0.02 g/cm ³
Sag / Slump	:	0 mm
Shrinkage (%)	:	< 10
Skin-forming time (at 27 °C/ 70% r.h)	:	7 -9 mins
Cure Time (to 3/8" @ 27 °C and 50% r.h)	:	5-7 days

Vulcanized Rubber

Tensile strength (ASTM D412)	:	1.17 MPa
Dynamic Joint Movement	:	+/- 25%
<small>(continue extension & compression 1/8" per hour)</small>		
Hardness Shore A (ASTM C920)	:	20-30
Elongation at Break (ASTM D412)	:	>500%
Application Temperature	:	-37°C to +60°C
Range Temperature resistance	:	-62°C to +150°C

Typical property data values should not used as specifications.

Characteristics :

- OCI E104 series silicone sealant are one part acetoxy silicone sealant which cures with atmospheric moisture to form a rubberlike seal for specialised glazing application, joint sealing and assembly.
- OCI E104 series silicone sealant are unaffected by high or low temperature and their physical properties are designed for outstanding durability and performance.

Application :

OCI E-104 sealants are suitable for use in :

- sealing
- bonding
- Repairing & Mending of glass
- Window contruction double glazing
- Aquarium
- Shower Screen
- Sanitary
- Air Conditioning
- Ventilator
- Bedding of marine hardwares

OCI E-104 silicone sealants exhibits an excellent adhesion to :

- glass
- tiles
- ceramics
- aluminium
- fiberglass
- non-oily woods
- painted surfaces
- Small glass water tanks

Technical Data Sheet



OCI E-104 ACETIC CURE SILICONE SEALANT

Product Code & Colour :

Product Code	Colour
OCI E-104	Black
OCI E-104	Clear
OCI E-104	White

Limitation :

Not for : Use in areas of constant water immersion

Not for : Traffic areas or areas subject to abrasion

Not for : Structural glazing

Not for : Bathroom

OCI E104 silicone sealants are not recommended for mirror installation without the approval of the mirror manufacturer.

Surface Preparation :

The silicone sealant should be applied at a thickness not to exceed 6 mm (1/4 in) from an exposed edge. The recommended minimum joint dimension is 1/4" x 1/4" and the maximum joint dimension is 1" x 3/8". Ensure all surface that will be in contact with the sealant must be clean, dry, free of dust, dirt, rust, oil and other contaminants. Non porous substrates should be clean with solvent and wipe dry immediately with cloth before the solvent evaporates from the surface. Porous surface should be roughen with a stiff-bristled brush, rubbed down or sandblasted.

Packaging, Storage & Shelf life :

- is available in 300 ml per cartridge.
- When stored in the original unopened container at temperature less than 27°C.
- a shelf life of 12 months from date of shipment.

Safety Precaution :

- Ensure good ventilation if used indoors.
- Contact of unvulcanized silicone sealant with eyes and mucous membranes must be avoided as this will cause irritation.
- Prolonged contact with eyes, flush with water and consult physician.
- Keep out of reach of children.
- Additional information is contained in our material safety data sheets available on request.
- Maximum recommended pressure for air operated guns with caulking cartridges is 45 psi (3.2kgs/cm³).

Other Information :

Every endeavor has been made to ensure that the information given herein is true and reliable but it is given only for the guidance of our customers. The company cannot accept any responsibility for loss or damage that may result from the use of the information, due to the possibility of variation of processing or working conditions and of workmanship outside our control. User are advised to confirm suitability of this product by their own tests.