

Technical Data Sheet



OCI HI-TEMP RED RTV

Physical Data :

Unvulcanized Rubber

Density	:	1.02 g/cm ³
Skin Over Time	:	5 to 20 mins

Vulcanized Rubber

Tensile strength (DIN 53504 S2)	:	approx. 2 MPa
Elongation at Break (DIN 53504 S2)	:	Min. 300 %
Hardness Shore A (DIN 53505)	:	20 to 30
100% Module (DIN 53504 S2)	:	approx 0.6 MPa
Shear Strength (aluminium) (DIN 53283)	:	approx 0.9 MPa
Shear Strength (Cr/Ni steel) (DIN 53283)	:	approx 0.8 MPa

measured after curing for 7 days at 23 °C in 50% RH

Characteristics :

- Hi-TEMP RTV is a non-slump acetoxy curing paste that cures to permanently flexible silicone rubber on exposure to atmospheric moisture at room temperature.
- The Hi-TEMP RTV exhibit an outstanding resistance to weathering, moisture, vibration, UV light.
- The product is heat stabilized and it is permanently flexible and stable at temperatures from -62°C to 343°C. It is also highly resistant to oil, transmission fluid and antifreeze.
- The RTV Red adheres to glass, metal, wood, painted surfaces, silicone rubber and some plastics. Since the composition of the substrates can vary greatly, adhesion tests for the specific case are advisable.

Application :

- Hi-TEMP RTV is a ready to use, solvent free silicone sealant which is primarily designed for general purposed sealing and bonding applications.
- Hi Temp RTV silicone makes reliable “formed-to place” gaskets that resist cracking, shrinking and migrating caused by thermal cycling. Ideal for use as replacement for gaskets, seals, gasket dressing, cork, felt, paper, rubber and asbestos gaskets.
- The consistency of the uncured material allows a high application rate and makes it good choice not only for dispensing from a caulking gun but also for automatic dispensing.
- The silicone rubber form from Hi-TEMP RTV is well suited for sealing joints that are exposed to high temperatures. The elasticity of the rubber remains unchanged over a wide temperature range from -60°C to 343°C.
- Hi-TEMP RTV is well suited as Formed-in-Place-Gasket (FIPG) material for flange sealing, for example on transmissions, compressors and pumps.
- Hi-TEMP RTV may also be used for :
 - Assembling valve and timing cover, crankcase, radiator, thermostat
 - Bonding gaskets in heating and cooling systems appliances.
 - Sealing connecting joints, flanged pipe joints.
 - Repairing cables.

Technical Data Sheet



OCI HI-TEMP RED RTV

Surface Preparation :

- Ensure all surfaces that will be in contact with the sealant must be clean, dry, free of dust, dirt, rust, oil and other contaminants.
- Nonporous substrates should be clean with solvent and wipe dry immediately with cloth before the solvent evaporates from the surface. Porous surfaces should be roughen with a stiff-bristled brush, rubbed down or sandblasted.
- Remove the gap and punch a hole on the tube with the gap's sharp edge. Cut off tip nozzle and screw on nozzle to tube.
- Apply on surface in steady flow by hand pressing.
- If required, smooth and shape sealant with spatula dipped in mild detergent.
- To remove excess uncured sealant with a mineral turpentine soaked cloth. Fully cured excess sealant can be removed by trimming with a sharp knife.
- Content fully cures in 48 hours.

For Best Results :

- To obtain a smooth and neat finish, apply masking tape and remove before sealant cures.
- Paint surfaces completely before applying sealant..

Safety Precaution :

- Ensure good ventilation if used indoors.
- Contact of unvulcanised silicone sealant with eyes and mucuous membranes must be avoided as this will cause irritation.
- Prolonged contact with eyes, flush with water and consult physician.
- Keep out of reach of children.
- Additional information is contained in our material safety data sheets available on request.
- Maximum recommended pressure for air operated guns with caulking cartridges is 45 psi (3.2kgs/cm³).

Storage :

- Store in dry and cool place below +30 °C.
- Use within 12 months from the date of Manufacturer.

Other Information :

Every endeavor has been made to ensure that the information given herein is true and reliable but it is given only for the guidance of our customers. The company cannot accept any responsibility for loss or damage that may result from the use of the information, due to the possibility of variation of processing or working conditions and of workmanship outside our control. User are advised to confirm suitability of this product by their own tests.